

1100S

Polypropylene (PP)

Description:

1100S is a Polypropylene Homo-polymer with the characteristic of balance stiffness and good impact. It is suitable for various applications like household and packaging. It also meets the F.D.A. requirement in the code of federal regulations in 21CFR 177.1520 for food contact.

Typical applications

Injection Molding : Packaging , Housewares and other

Physical Properties:	Method	Unit	Value
Melt Flow Index (2.16 kg/230°C)	ASTM D1238	g/10min.	30
Tensile Strength at Yield	ASTM D638	N/mm ²	36
Elongation at Yield	ASTM D638	%	28
Izod Notched Impact Strength (at 23°C)	ASTM D256	J/m	28
Flexural Modulus (1% SECANT)	ASTM D790	MPa	1350
Rockwell Hardness	ASTM D785	R-Scale	105
Heat Distortion Temperature (Load 0.45 N/mm ²)	ASTM D 648	°C	100

Processing Technique

Processing Temperature : 190 – 240 °C

However, the actual processing conditions depend on mold design, power of machine, equipment and other environments.

Remark: The values presented on the above are typical laboratory average, not to be construed as specifications and may vary within moderate ranges. The applicability or the accuracy of this information or the suitability of our products cannot be guaranteed because the conditions of use on the part or our uses are beyond our control.